PRELIMINARY TECHNICAL DATA SHEET

ECKART Effect Pigments

REVISION: **0** EDITION: **March 2008** IDENT-NO.: **FH.4213.1**

Product denomination: **Pearlescent Pigment PRESTIGE Glamour Red Gold**

Article number: **35449..**
Product description: **Free flowing powder with a red golden reflection colour comprising platelets of mica coated with titanium dioxide and iron oxide**

test criteria	nominal	unit	test method
Assay			
mica	**72 - 88**	**%**	**ECKART**
titanium dioxide	**9 - 17**	**%**	**ECKART**
iron oxide	**3 - 11**	**%**	**ECKART**
particle size range	**20 - 150**	**µm**	**Laser diffraction**
pH of 10 % aqueous suspension	**7 - 11**		**ISO 787-9**
Heavy metals			
antimony	**<= 0,0002**	**%**	**ECKART**
arsenic	**<= 0,0001**	**%**	**ECKART**
cadmium	**<= 0,0001**	**%**	**ECKART**
lead	**<= 0,0010**	**%**	**ECKART**
mercury	**<= 0,0001**	**%**	**ECKART**
visual and colorimetric evaluation	**conforms**		**ECKART**
tot. amount of bacteria	**<= 30**	**cfu/g**	**ECKART**
yeast and mould	**<= 30**	**cfu/g**	**ECKART**
pathogens	**negative**		**ECKART**

EC-Safety data sheet no.: PRES2

Other remarks:

INCI names	CI No.	CAS No.	EINECS No.
mica		12001-26-2	310-127-6
titanium dioxide	77891	13463-67-7	236-675-5
iron oxide	77491	1309-37-1	215-168-2

"The Data on this technical information sheet correspond with the current status of our knowledge and experience. The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights. We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process."

For more information and samples, please contact:
ECKART GmbH
Kaiserstraße 30
D-90763 Fürth/Bayern
Telephone: +49 (0) 91 52 / 77-49 10
Telefax: +49 (0) 91 52 / 77-49 18

depart., name: Finland, Pekka Eskelinen | date,approved: 06.03.2008 signed Pekka Eskelinen